



# Determining how much Hardfacing is required.



[www.hardfacetechnologies.com](http://www.hardfacetechnologies.com)

[www.hardfacetechnologies.com/postle\\_hft\\_btsp/pdfs/amount-of-hardfacing-required.pdf](http://www.hardfacetechnologies.com/postle_hft_btsp/pdfs/amount-of-hardfacing-required.pdf)

cylindrical. In arriving at the final weight of weld deposit make sure you consider the deposit efficiency of the welding process.

- Stick Electrode - 65% • Tubular Electrode 90% • Bare TIG - 98%
- Metal Core Wire - 95% • Flux-Cored Wire - 90%

**Squares and Rectangles:** Length x Width x Depth x (0.3) = Weight of Weld Deposit

**Table 1 - Weight of Weld deposit - Flat Work** - To estimate total weight of deposit, multiply weight per square inch by the number of square inches to be overlaid.

Thickness of Deposit	1/8	1/4	3/8	1/2	3/4
Pounds per Square Inch	0.038	0.075	0.113	0.15	0.225

**Example:** Welded areas - 12 inch x 2 inch at 1/4 weld thickness with a Tubular Electrode

$$(12 \times 2 \times 1/4 \times 0.3) = 1.8 \text{ divided by } 90\% \text{ (welding process deposit efficiency)} = 2 \text{ pounds of welding alloy}$$

**Cylinders:** 3.1416 x Diameter x Depth x (0.3) = Weight of Weld Deposit

**Table 2 - Weight of Weld Deposit - Cylindrical Components** - To estimate total weight of deposit, multiply weight found below by the length (in inches) of the work to be overlaid.

Diameter of Work (Inches)	Weight (pounds per inch of length)			Thickness of Deposit (inch)		
	1/8	1/4	3/8	1/2	5/8	3/4
4	0.47	0.94	1.41	1.88	2.36	2.83
5	0.59	1.18	1.77	2.36	2.95	3.53
6	0.71	1.41	2.12	2.83	3.53	4.24
7	0.82	1.65	2.47	3.30	4.12	4.95
8	0.94	1.88	2.83	3.77	4.71	5.65
9	1.06	2.12	3.18	4.24	5.30	6.36
10	1.18	2.36	3.53	4.71	5.89	7.07
11	1.30	2.59	3.89	5.18	6.48	7.78
12	1.41	2.83	4.24	5.65	7.07	8.48
14	1.65	3.30	4.95	6.60	8.25	9.90
16	1.88	3.77	5.65	7.54	9.42	11.31
18	2.12	4.24	6.36	8.48	10.60	12.72
20	2.36	4.71	7.07	9.42	11.78	14.14
24	2.83	5.65	8.48	11.31	14.14	16.96
28	3.30	6.60	9.90	13.19	16.49	19.79
32	3.77	7.54	11.31	15.08	18.85	22.62
36	4.24	8.48	12.72	16.96	21.21	25.45
40	4.71	9.42	14.14	18.85	23.56	28.27
48	5.65	11.31	16.96	22.62	28.27	33.93
60	7.07	14.14	21.21	28.27	35.34	42.41

**Example:** Welded area - A 10 inch diameter cylinder, 12 inches long at a 1/4 inch weld thickness with a Tubular Electrode. 2.36 x 12 inches divided by 90% (welding process deposit efficiency) = 31.46 pounds of welding alloy.